

SUNSET FALLS ** GLAZED PORCELAIN FLOOR AND GLAZED CERAMIC WALL & MOSAIC WITH REVEAL IMAGING**

Invite the calming effects of the sun setting over the water into your design. With a natural travertine stone-look and gentle linear grain, Sunset Falls provides classic style in timeless tones. Rectangular shapes in several sizes and a herringbone mosaic offer plenty of flexibility for foundational neutrality or a monochromatic vibe.

GLAZED PORCELAIN FLOOR TILE





WHITE SF15

BEIGE SF16



GRAY SF17

GLAZED CERAMIC WALL TILE







GLAZED CERAMIC MOSAIC







JOLLY TRIM

BEIGE SF16

GRAY SF17



WHITE SF15











SUNSET FALLS ™ GLAZED PORCELAIN FLOOR AND GLAZED CERAMIC WALL & MOSAIC WITH REVEAL IMAGING®

SIZES

		THICKNESS	SQ. FT./ CARTON	PIECES/ CARTON
12 x 24 Floor Tile	11-13/16" x 23-13/16" (30.00 cm x 60.48 cm)	5/16"	17.37	9
	6" x 18" (15.26 cm x 45.77 cm)	3/8"	11.25	15
4 x 12 Wall Tile □	4-1/4" x 12-7/8" (10.91 cm x 32.77 cm)	5/16"	10.64	28
1 x 3 Herringbone Mosaic □■	9" x 12" Sheet (22.86 cm x 30.48 cm Sheet)	1/4"	6.00	10

TRIM

			NUMBER	PIECES/ CARTON
	Floor Bullnose	3 x 24	P-43F9	10
	Jolly	1/2 x 12	S1/212J	6 CARDS*
☐ Ceramic body	■ Dot-mounted	* 4 pieces per card		

INSTALLATION & PRICING

RECOMMENDED GROUT JOINT:

Floor: 3/16" (Overlap should not exceed 33% when installing tile with a length 15" or greater in a staggered brick-joint pattern.)

Wall: $(6 \times 18) 1/16$ " (1/8" when rectangular size is installed in a staggered brick-joint pattern; overlap should not exceed 33%.)

 (4×12) 1/16" (When rectangular size is installed in a staggered brick-joint pattern, overlap should not exceed 33%.)

Mosaic: 1/8"

RELATIVE PRICING: Medium

SHADE VARIATION



PERFORMANCE CHARACTERISTICS

	ASTM#	FLOOR RESULT	WALL RESULT	MOSAIC RESULT
Water Absorption	C373	< 0.5%	< 20.0%	< 3.0%
Breaking Strength	C648	> 275 lbs.	120-230 lbs.	> 250 lbs.
Scratch Hardness	MOHS	8.0	4.0-6.0	7.0
Chemical Resistance	C650	Resistant	Resistant	Resistant
Abrasion Resistance	C1027	3	N/A	3

For additional information on test results, visit us at: americanolean.com/information/TestResults.

USAGE

FLOORS	WALLS	COUNTERTOPS
F	W	С

APPLICATIONS

	TARGET DCOF WET	SUITABLE
Dry & Level – Interior Floor	N/A	•
Wet & Level – Interior Floor	≥ 0.42	•
Shower Floors (Residential or Light Commercial)	≥ 0.42	•**
Exterior Floor Applications (including pool decking & other wet areas with minimal footwear)	≥ 0.60	
Ramps & Inclines	≥ 0.65	
Walls/Backsplashes	N/A	•
Countertops	N/A	•
Pool Linings	N/A	•"

A DCOF value of \geq 0.42 is the standard for tiles specified for level interior spaces expected to be walked upon when wet, as stated in ANSI A137.1-A326.3. For more information about DCOF and the DCOF AcuTestTM, visit americanolean.com/DCOF.

APPLICATION NOTES:

Floor tile suitable for exterior applications in freezing and non-freezing climates, when proper installation methods are followed.

Wall and mosaic tile suitable for exterior applications in non-freezing climates, when proper installation methods are followed.

- * Wall tile not suitable for this application.
- ** Mosaic tile only

NOTES

Since there are variations in all fired ceramic and natural products, tile and trim supplied for your particular installation may not match samples. Final confirmation should be made from actual tiles and trim prior to installation. Manufactured in accordance with ANSI Al37.1 standards.

Not for use on ramps. Water, oil, grease, improper drainage and certain footwear can create slippery conditions. Floor applications expected to be exposed to these conditions require extra caution in product selection.

For additional information refer to "Factors to Consider" at: americanolean.com/Factors.

Special consideration needs to be given when installing tiles greater than 15 inches. Please refer to americanolean.com/LargeTiles for more information.

Use of a latex modified thin-set is recommended for installation. For more information, visit americanolean.com.







