


MARAZZI  **USA**

the fine art of ceramic tile

(province)

glazed ceramic tile

Made In The USA



New Brunswick



Nova Scotia



Quebec



New Brunswick Mosaic - Square 2"x2"







Nova Scotia Mosaic - Square 2"x2"



Quebec Mosaic - Square 2"x2"



FLOOR TILE	DECOS*	TRIMS**
		
12"x12" (30x30 cm)	18"x18" (45x45 cm)	12"x12" (30x30 cm)
5/16" (7.5mm)	5/16" (8.5mm)	Mosaic - Square 2"x2"
		
		3"x12" (8x30 cm)
		Bullnose







Thickness

Names (colors)

New Brunswick (Ivory)	ULCT	ULCX	ULD3	ULD7
Nova Scotia (Rust)	ULCU	ULCY	ULD4	ULD8
Quebec (Walnut)	ULCV	ULCZ	ULD5	ULD9

Notes: * Mosaics are mounted to mesh backing.

** Trim is available in all colors and made to complement Floor Tile.

-  Floor Tile
-  Wall Tile
-  Decorative Tile
-  Trim Available
-  Slight Variation
-  Frost Resistant

-  Abrasion Resistance
-  D.C.O.F. (Wet Areas)
(Minimum 0.42)
-  S.C.O.F. (Wet)
(Valid through 12-31-2013)
-  S.C.O.F. (Dry)
(Valid through 12-31-2013)
-  7% Minimum Pre-Consumer Recycled Content
-  No VOC



Contributes to
LEED Credits

made in the
USA

ASTM TEST RESULTS

Technical Characteristics	ANSI Standards	ASTM Test Results	ASTM Test Methods
Water Absorption	3.0% - 7.0%	2.0% - 5.0%	C373
Frost Resistance	As Reported	Resistant	C1026
Scratch Resistance	MOHS 1-10	7	MOHS Scale
Breaking Strength	≥ 250 lbf.	≥ 385 lbf.	C648
Facial Dimension	-3.0% ≤ Nominal ≤ 3.0%	Within Standard	C499
Nominal Thickness	≤ 0.04 in (1.02 mm max)	Within Standard	C499
Wedging (squareness)	+/- 0.50% or +/- 2.0 mm**	Within Standard	C502
Warpage (flatness)	+/- 0.75% or +/- 2.0 mm**	Within Standard	C485
Abrasion Resistance	Class 0 - Class V	Class IV	C1027
DCOF-Dynamic Coefficient of Friction (Wet Areas Only)*	As Reported	Minimum 0.42	DCOF AcuTest SM *
SCOF-Static Coefficient of Friction (Dry)	As Reported	0.70 ≤ S.C.O.F. < 0.80	C1028
SCOF-Static Coefficient of Friction (Wet)	As Reported	0.50 ≤ S.C.O.F. < 0.60	C1028
Chemical Resistance	Class A - Class E	Class A	C650
Stain Resistance	Class A - Class E	Class A	C1378



* Dynamic Coefficient of Friction (DCOF) - Water, oil, grease or other fluids create slippery conditions. When installing floors in areas with exposure to these conditions, a minimum D.C.O.F. value of 0.42 is required. Additionally, extra caution is required with regards to product selection and proper maintenance. Visit www.tcnatile.com for complete information regarding the DCOF AcuTestSM test method and values.

* DCOF AcuTest is the industry designation for the test procedure contained in ANSI A137.1 Section 9.6, which has been extensively researched, allows for in-situ field measurements, and is in use at tile manufacturing facilities. It was so named to distinguish it from other DCOF measurements using different instruments and/or protocols.